



Condensed-Phase Processes During Solid Propellant Combustion. IV. Chemical and Microscopic Examination of Laser-Irradiated Propellant Samples

M. A. Schroeder
R. A. Beyer
A. Cohen
R. A. Fifer
R. A. Pesce-Rodriguez

ARL-TR-781

July 1995



19950830 085

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION IS UNLIMITED.

DTIC QUALITY INSPECTED 5

NOTICES

Destroy this report when it is no longer needed. DO NOT return it to the originator.

Additional copies of this report may be obtained from the National Technical Information Service, U.S. Department of Commerce, 5285 Port Royal Road, Springfield, VA 22161.

The findings of this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

The use of trade names or manufacturers' names in this report does not constitute endorsement of any commercial product.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE July 1995	3. REPORT TYPE AND DATES COVERED Final, Oct 91-Oct 92		
4. TITLE AND SUBTITLE Condensed-Phase Processess During Solid Propellant Combustion. IV. Chemical and Microscopic Examination of Laser-Irradiated Propellant Samples		5. FUNDING NUMBERS PR: 1L161102AH43		
6. AUTHOR(S) M. A. Schroeder, R. A. Beyer, A. Cohen, R. A. Fifer, and R. A. Pesce-Rodriguez				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRL-WT-PC Aberdeen Proving Ground, MD 21005-5066		8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-781		
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES)		10. SPONSORING / MONITORING AGENCY REPORT NUMBER		
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.		12b. DISTRIBUTION CODE		
13. ABSTRACT (Maximum 200 words) The surfaces of laser-irradiated gun propellants have been examined by scanning electron microscopy (SEM) and Fourier Transform Infrared (FTIR) microscopy. The results suggest that the laser-irradiated surfaces exhibit chemical and physical changes similar to those exhibited by the burned surfaces of propellant samples, the combustion of which have been quenched short of completion. Some possible implications of this for combustion and for the modelling of laser ignition are discussed.				
14. SUBJECT TERMS propellants, gun propellants, XM39, M9, M10, M30, JA2, laser ignition, laser pyrolysis, combustion, ignition, pyrolysis, burning surfaces			15. NUMBER OF PAGES 32	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

INTENTIONALLY LEFT BLANK.

PREFACE

This report is the fourth in a series of reports examining the chemical and microstructural nature of several burned propellant samples. While this investigation was in progress, the U.S. Army Ballistic Research Laboratory (BRL) was deactivated and became part of the U.S. Army Research Laboratory (ARL).

Accession For	
HTIS GRA&I	<input checked="checked" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution	
Availability Codes	
Dist	Avail and/or Special
A-1	

INTENTIONALLY LEFT BLANK.

ACKNOWLEDGMENT

The authors are grateful to Robert J. Lieb for helpful discussions and for the use of some of his equipment, including a drop-hammer apparatus for splitting propellant grains. The work described here could not have been accomplished without equipment provided by the Productivity Enhancement Capital Investment Program.

INTENTIONALLY LEFT BLANK.

TABLE OF CONTENTS

	<u>Page</u>
PREFACE	iii
ACKNOWLEDGMENT	v
LIST OF FIGURES	ix
LIST OF TABLES	xi
1. INTRODUCTION	1
2. EXPERIMENTAL	2
3. RESULTS	3
4. DISCUSSION AND CONCLUSIONS	3
4.1 Examination of Laser-Irradiated Samples: SEM	3
4.2 Examination of Laser-Irradiated Samples: FTIR Microscopy	6
4.3 Comparison of Laser-Irradiated and Burned/Extinguished Samples	7
5. RECOMMENDATIONS FOR FUTURE RESEARCH	8
6. REFERENCES	19
DISTRIBUTION LIST	21

INTENTIONALLY LEFT BLANK.

LIST OF FIGURES

<u>Figure</u>	<u>Page</u>
1. Overall view of portion of laser-irradiated grain of XM39 propellant	10
2. Cross section of melt layer of laser-irradiated grain of XM39 propellant	10
3. Overall view of portion of laser-irradiated grain of M30 propellant	11
4. Cross section of melt layer of laser-irradiated grain of M30 propellant	11
5. Top of melt layer of laser-irradiated grain of M30 propellant	12
6. Overall view of portion of laser-irradiated grain of M9 propellant	12
7. Cross section of surface layers of laser-irradiated grain of M9 propellant	13
8. Overall view of portion of laser-irradiated grain of M10 propellant	13
9. Cross section of surface layers of laser-irradiated grain of M10 propellant	14
10. Overall view of portion of laser-irradiated grain of JA2 propellant	14
11. Cross section of surface layers of laser-irradiated grain of JA2 propellant	15
12. FTIR microscope spectrum of irradiated portion of grain of M9 propellant	15
13. FTIR-microscope spectra of (a) laser-irradiated M9 (Sample no. 115, Table 2) propellant; (b) burned/extinguished M9 propellant (Schroeder et al. 1994); and (c) virgin M9 propellant	16
14. FTIR-microscope spectra of (a) virgin JA2 propellant; (b) laser-irradiated JA2 propellant (sample no. 24, Table 2); and (c) burned/extinguished JA2 propellant (Schroeder et al. 1994)	16
15. FTIR-microscope spectrum of virgin XM39 propellant	17
16. FTIR-microscope spectra of (a) laser-irradiated (sample no. 58, Table 2) XM39 propellant; (b) laser-irradiated (sample no. 33, Table 2) XM39 propellant; and (c) virgin XM39 propellant	17

INTENTIONALLY LEFT BLANK.

LIST OF TABLES

<u>Table</u>		<u>Page</u>
1.	Compositions of Propellant Formulations Studied	4
2.	Conditions of Laser-Irradiation of the Samples Studied	4
3.	Summary of Observations for Compositions Studied	5

INTENTIONALLY LEFT BLANK.

1. INTRODUCTION

This is a progress report on work aimed at understanding the nature and importance of condensed phase reactions in the combustion of nitramine and other solid gun propellants. Information on the nature and importance of condensed phase reactions is needed as input for modelling studies. This information could also be very important in understanding the relationship of chemical structure and of physical properties such as melting points, phase transition temperatures, etc., to explosive and propellant behavior.

Our previous work on burned propellants has been described in three reports (Schroeder et al. 1990, 1992, and 1994). In that work, burning propellant samples were quenched, and the burned surfaces were examined both microscopically and by chemical analysis (Schroeder et al. 1990, 1992). Studies (Schroeder et al. 1990, 1992) were carried out on a series of propellants and compositions including XM39, M30, JA2, RDX, and the HMX/binder composition HMX2. Preliminary results (Schroeder et al. 1990) on XM39 were consistent with the idea that at least at low pressures there is a liquid layer approximately 100–300 μm thick in combustion of nitramine propellants; scanning electron microscopic (SEM) examination revealed little if any evidence of degradation below this layer. Gas chromatography mass spectroscopy (GCMS) analysis (Schroeder et al. 1990, 1992) suggests that the stabilizer is considerably depleted relative to the plasticizer in the surface layers, presumably by reaction with nitrogen oxides formed by decomposition of RDX and NC. High-performance liquid chromatography (HPLC) results suggest that there is a significant increase in concentration of the mechanistically significant nitrosoamines MRDX and DRDX over the very small amounts possibly present as impurities in RDX. The structures of these nitrosoamines are similar to that of RDX, with respectively one or two nitro groups replaced by nitroso groups. These results are consistent with the idea that RDX decomposition under propellant combustion conditions involves primarily (a) vaporization followed by gas-phase decomposition and/or (b) decomposition in the liquid phase to products that are almost entirely gaseous. Photoacoustic Fourier transform infrared (FTIR-PAS) examination (Schroeder et al. 1990, 1992) of the burned surfaces also provided evidence for condensed-phase reaction in the compositions studied. Results of SEM examination of the burned surfaces of quenched samples of HMX2, HMX/PU, RDX, M30, and JA2 were also presented (Schroeder et al. 1990, 1992). Some depth-profiling results have also been reported (Schroeder et al. 1994).

In the present report, a somewhat different departure is described. A series of laser-irradiated propellant samples have been obtained in the course of studies (Beyer and Cohen 1992) on laser ignition

of gun propellants. Each of these samples consists of a grain of propellant marked by a cavity several millimeters wide and several millimeters deep where the grain was struck by the laser beam. During laser irradiation, the sample appeared to burn, but combustion ceased on deradiation. The inside surfaces of the cavities are being examined by SEM, optical microscopy, and by chromatographic and spectroscopic methods.

The reasons for studying these samples are as follows: (a) they are pertinent to our work because it seems relevant to our understanding of the combustion process to see whether the effect of exposing a propellant surface to any external heat source, such as a laser, will be similar to the effect of the combustion process as revealed by our previous studies; (b) our access to the strand burner needed for the continuation of our regular work was delayed due to the press of other work; and (c) an examination of these surfaces was of interest to workers at ARL who are engaged in the study of laser ignition.

2. EXPERIMENTAL

Laser irradiation (Beyer and Cohen 1992) of the samples was carried out on a continuous-wave CO₂ (10.6 μ m) laser (Synrad model #57) with variable power (nominal 10–100 W) used as the ignition source. Data were obtained for the following propellants: M9 (homogeneous double base), M30 (composite triple base), XM39 (RDX composite), and HMX2 (HMX composite). The samples were small disks approximately 0.19 in wide. The M30 and XM39 disks were cut from 0.25-in-diameter grains (perforated and with graphite surfaces), and the others were cut from 0.25-in-diameter strands. The beam, having about a 0.118-in diameter, was directed along the propellant axis and covered approximately 25% of the sample surface. Pulse lengths were varied from 0.1 to 15 s. Irradiation was carried out in either open air or in a closed 1-l bomb.

The irradiated grains were cooled to dry ice temperatures and split with a knife blade held vertical by mechanical means; when this knife blade was rested against the propellant grain and struck by a hammer, a clean split could be obtained (the knife was mechanically prevented from penetrating more than a small fraction of the grain). One half of the split grain was kept for spectroscopic and chromatographic examination, and the other half was examined by SEM.

The SEM microscope used was a JEOL Model JSM-820 instrument. Samples were sputtered with gold before examination.

FTIR-microscope spectra were obtained with 8-cm^{-1} resolution and 1,024 scans, using a Spectra-Tech IR-Plan infrared microscope, operating in reflectance mode and interfaced to a Mattson Polaris FTIR spectrometer operated through a PC running Mattson FIRST software. Where necessary, the Kramers-Kronig transformation was used to remove spectral distortions. Spectra were obtained on unirradiated propellant surfaces and on the center (bottom) surface of the crater made by the laser beam. The area sampled was a square $400\text{ }\mu\text{m}$ on a side.

3. RESULTS

The samples examined were taken from a series of samples that had been irradiated in connection with studies in progress at ARL (Beyer and Cohen 1992). These samples had been irradiated with a laser of known power for known lengths of time; during irradiation a jet of flame shot out from the sample, but it disappeared on deradiation (i.e., when the laser was turned off), leaving a crater where the sample was struck by the laser beam. A large number of samples were available; however, because of time limitations, only a limited number were chosen. For the preliminary study described here, a series of samples with moderate damage (medium-sized craters) was chosen and examined by SEM and by FTIR microscopy.

Table 1 gives the compositions of the propellants studied, and Table 2 gives the conditions under which laser-irradiation of the various samples took place.

SEM microscope photos are shown in Figures 1–11, and FTIR spectra are shown in Figures 12–16.

Our observations from the study of these samples are summarized in Table 3. FTIR-microscope examination of the M10 and M30 samples has not yet been carried out.

4. DISCUSSION AND CONCLUSIONS

4.1 Examination of Laser-Irradiated Samples: SEM. Figures 1 and 2 respectively show an overall view of a laser-irradiated grain (no. 33, Table 2) of XM39 propellant, and a close-up view of part of the melt layer. The surface is covered with debris that looks as though it might be decomposed binder, and there is a melt layer which contains numerous bubbles and averages several hundred micrometers in

Table 1. Compositions of Propellant Formulations Studied

Propellant	Ingredient	Composition (%)
XM39	RDX	76.0
	Cellulose Acetate Butyrate (CAB)	12.0
	Acetyl Triethyl Citrate (ATEC)	7.6
	Nitrocellulose (NC) (12.6% N)	4.0
	Ethyl Centralite (EC)	0.4
M30	Nitroguanidine (NQ)	47.7
	Nitrocellulose (NC) (12.68% N)	28.0
	Nitroglycerine (NG)	22.5
	Ethyl Centralite (EC)	1.5
	Cryolite	0.3
JA2	Nitrocellulose (NC) (13.04% N)	59.5
	Diethylene Glycol Dinitrate (DEGDN)	14.9
	Nitroglycerine (NG)	24.8
	Ethyl Centralite (EC)	0.7
	Magnesium Oxide	0.05
	Graphite	0.05
M9	Nitrocellulose (NC) (13.29% N)	57.75
	Nitroglycerine (NG)	40.00
	Ethyl Centralite	0.75
	Potassium Nitrate	1.50
M10	Nitrocellulose (NC) (13.16% N)	98.00
	Potassium Sulfate	1.00
	Diphenylamine	1.00

Table 2. Conditions of Laser Irradiation of the Samples Studied

Sample No. and Propellant	Atmosphere	Laser Power (W)	Time (ms)
24 (JA2)	Air	1.7	2,700
33 (XM39)	Air	1.2	1,216
46 (M30)	Air	1.7	1,628
58 (XM39)	Air	41.0	384
90 (M9)	Air	114.0	117
105 (M10)	N ₂	34.3	260
106 (M10)	Air	34.3	300
115 (M9)	N ₂	1.8	1,082

Table 3. Summary of Observations for Compositions Studied

Propellant	Melt Thickness (μm)	General Conclusions (This Study)
XM39	100–300	Surface Color: Off-white to yellow/orange at bottom, black inside rim. Melt layer contains bubbles and signs of crystallization and is covered in places with debris. FTIR-Microscopy: Shows increase in carbonyl ($>C=O$) peak due to binder and its decomposition products.
M30	10–20	Surface Color: Dirty brown, much less black inside rim than in the case of XM39. Melt layer contains bubbles and is covered in places with debris.
M9	10	Surface Color: Same as bulk propellant. Melt layer smooth, contains some bubbles and cracks. FTIR-Microscopy: Irradiation causes appearance of $>C=O$ peak.
M10	10	Surface Color: Dirty brown or (one sample) yellow green; some flecks of brown. Melt layer has more bubbles than in case of M9.
JA2	10	Surface Color: Same as bulk propellant (yellow-orange). Melt layer has more bubbles than in case of M9. FTIR-Microscopy: Irradiation causes appearance of $>C=O$ peak.

thickness. The bubbles presumably arise from decomposition, especially of RDX, and are probably indicative of condensed-phase decomposition of RDX oxidizer. A closer view of the melt layer (Figure 2) shows the presence of what appear to be crystals, presumably from crystallization of molten RDX on cooling and solidification. The irradiated surface layers here resemble those (Schroeder et al. 1990) of XM39 propellant burned in air at atmospheric pressure and quenched by dropping in water.

Figures 3–5 respectively show an overall view and some closeups of a laser-irradiated grain (no. 46, Table 2) of M30 propellant. A cross section of the burned surface (Figure 4) shows a very thin bubbly melt layer, at most 10–20 μm thick. As in the case of XM39, the bubbles presumably arise from decomposition and are probably indicative of condensed-phase decomposition. The top of the surface appears bubbly (Figure 5) and is partially covered with debris (Figure 3). Thus, as in the case of XM39, the irradiated surface of M30 generally resembles that (Schroeder et al. 1992) of M30 propellant burned in air at atmospheric pressure and quenched by dropping it in water. One difference is the presence of

small amounts of fuzzy material in places on the surface of the laser-irradiated M30 sample; this is possibly nitroguanidine or its decomposition products that have sublimed, then condensed on quenching by deradiation.

Figures 6 and 7 respectively show an overall view of an irradiated grain of M9 propellant and a closeup of the irradiated surface. The "hills" or "steps" inside the crater (Figure 6) are possibly the result of some inhomogeneity in the laser beam. The surface appears generally smooth, although covered in places with bubbles (condensed-phase decomposition), cracks, and flecks of debris. The melt layer appears very thin, about 10 μm at most; this is consistent with the results of depth profiling studies (Schroeder et al. 1994) on M9.

Figures 8 and 9 respectively show an overall view of a laser-irradiated grain of M10 propellant and a closeup of the cross-section of the burned surface. The surface appears covered with bubbles (condensed-phase decomposition), and the melt layer is quite thin, no more than 10 μm or so thick; these observations are consistent with the behavior of the nitrate ester compositions M9 and JA2 in combustion (Schroeder et al. 1992, 1994) and laser-irradiation (present work) conditions.

Figures 10 and 11 respectively show an overall view of a laser-irradiated grain of JA2 propellant and a cross section of the melt layer taken on the same grain. Again, the surface appears covered with bubbles (condensed-phase decomposition), and the melt layer is quite thin (no more than 10 μm or so thick); this is consistent with the behavior of the nitrate ester compositions M9 and M10 under combustion (Schroeder et al. 1992, 1994) and laser-irradiation (present work) conditions.

4.2 Examination of Laser-Irradiated Samples: FTIR Microscopy. Figure 12 shows an FTIR-microscope spectrum of the laser-irradiated surface of a grain of M9 propellant, and Figure 13 shows a comparison among a laser-irradiated grain of M9 Propellant, a burned/extinguished (Schroeder et al. 1994) grain of M9 propellant, and an FTIR-microscope spectrum of virgin M9. The changes in the spectra on laser irradiation and on burning/extinguishment are almost the same, consisting of the appearance of weak absorption in the carbonyl region at approximately $1,730\text{ cm}^{-1}$ and possibly of a slight increase in the C-O-C bands in the $1,000\text{--}1,200\text{-cm}^{-1}$ region.

Figure 14 shows a similar comparison for JA2 propellant. The spectrum quality of the laser-irradiated sample is not as good as the others, but the appearance of the carbonyl ($>\text{C}=\text{O}$) band in the $1,730\text{-cm}^{-1}$

region can be seen. These changes are believed to be due to loss of NO_2 due to O-N cleavage of the nitrate ester groupings during initial decomposition of the nitrate ester ingredients of these propellants (Table 1); this would result in a decrease in intensity of the NO_2 bands relative to the skeletal C-O-C bands; furthermore, the alkoxy radical left behind might be expected to ultimately lead to an aldehyde or ketone grouping, having (Gordon and Ford 1972; Silverstein, Bassler, and Morrill 1991) characteristic absorption in the region around $1,720\text{ cm}^{-1}$.

Figure 15 shows FTIR-microscope spectra of virgin XM39 propellant, and Figure 16 shows two different irradiated grains of XM39 propellant. Note that although they differ in similar ways from the spectrum of virgin XM39, the two spectra of irradiated XM39 are not identical to each other; thus it appears that the duration and intensity of the laser pulse have some effect on the extent of the chemical changes observed by FTIR microscopy. Comparison with the surface spectra (Schroeder et al. 1994) of burned/extinguished samples suggests that the changes on irradiation and on burning tend to be similar but that more RDX remains on the surface of the laser-irradiated samples. These changes are possibly due to accumulation of the CAB binder and its decomposition products at the burning surface as the decomposition proceeds, as described in Schroeder et al. (1994). Note, however, that the possible effect of differences in absorption coefficients of the RDX and of the binder for the laser light has not been examined.

4.3 Comparison of Laser-Irradiated and Burned/Extinguished Samples. The SEM studies indicate that with regard to melt layer thickness, presence of bubbles, etc., the results to date are in general agreement with our earlier results (Schroeder et al. 1990, 1992, and 1994) for the surfaces of burned/quenched propellant samples.

In addition, the results of FTIR-microscope analysis of the inside, laser-irradiated surfaces of the cavities suggest that the chemical changes in the irradiated layers are similar in nature to those observed earlier for quenched surfaces of burned/quenched propellant samples.

The results described here seem most consistent with the idea that the principal interaction of the laser beam with the sample is thermal in nature. This is suggested by (a) the presence of the melt layer in all samples, as shown by the presence of bubbles and (in the case of XM39) of crystallization of melted RDX; and (b) the similarity in appearance between the burned/extinguished surfaces (Schroeder et al. 1990, 1992) and the laser-irradiated surfaces described here.

The similarity between laser-irradiated and burned/extinguished propellant surface layers is of interest because it suggests that, in both cases, the changes in the surface layers are caused by the imposition of a heat source from above. In the case of the burned/extinguished samples, the heat is generated by the reaction of gaseous products of decomposition of the propellant ingredients, while in the case of the laser-irradiated samples, the external heat is presumably due partly to the laser beam itself and partly to heat generated by reaction (combustion) between gaseous products of laser-induced decomposition of the propellant ingredients. This makes sense if, as seems reasonable (Ostmark and Grans 1990; Ostrowski et al. 1980) (see also the preceding paragraph), the effect of the laser on these samples was primarily thermal in nature.

Another interesting point from these studies is that they demonstrate the presence of a melt layer in these samples. Since models of laser ignition have had only partial success (Beyer and Cohen 1992) in predicting times to emission, times to flamespreading and times to pressure buildup, this suggests that it might be helpful to modify existing laser ignition models to take into account the existence of the liquid layer.

5. RECOMMENDATIONS FOR FUTURE RESEARCH

Further laser-irradiated samples should be examined in order to evaluate the effect on the results of such factors as atmosphere, laser-pulse power, and duration.

Runs should be carried out in a strand burner with depressurization-quenching, and the results should be compared with those from the quenching methods used to date.

Optical microscope examination of the burned surfaces should be carried out, particularly in view of the possibility that studies of color changes and variations may yield information on the occurrence (or lack thereof) of chemical changes in the solid below the liquid layer.

Additional methods for depth-profiling of the burned layers are being explored; these include microabrasive blasting, microtoming, solvent-dipping, and improved scraping procedures. Depth-profiling should be applied to the nitrosoamine-formation and stabilizer-depletion results reported previously (Schroeder et al. 1990, 1992). Additional binders, oxidizers, and formulations should be studied.

Isotope-scrambling studies on burning (rather than merely decomposing) samples are needed. These would involve use of mixtures of unlabelled RDX or HMX with RDX or HMX labelled with nitrogen-15 in all nitrogens, both in the ring and in the nitro groups. Use of these mixtures would lead to scrambled nitrosoamines if the recombination mechanism were operating, but to unscrambled nitrosamines if an oxygen-abstraction mechanism were operating. Partial scrambling might mean that both mechanisms were operating to some degree. Note, however, that while formation of fully scrambled nitrosoamines would provide no evidence for oxygen abstraction, it would not necessarily rule it out, since the scrambling could have taken place by further N-N cleavage equilibria before or after formation of the nitrosoamines.




Figure 1. Overall view of portion of laser-irradiated grain of XM39 propellant.




Figure 2. Cross section of melt layer of laser-irradiated grain of XM39 propellant.




Figure 3. Overall view of portion of laser-irradiated grain of M30 propellant.




Figure 4. Cross section of melt layer of laser-irradiated grain of M30 propellant.




Figure 5. Top of melt layer of laser-irradiated grain of M30 propellant.




Figure 6. Overall view of portion of laser-irradiated grain of M9 propellant.




Figure 7. Cross section of surface layers of laser-irradiated grain of M9 propellant.




Figure 8. Overall view of portion of laser-irradiated grain of M10 propellant.




Figure 9. Cross section of surface layers of laser-irradiated grain of M10 propellant.




Figure 10. Overall view of portion of laser-irradiated grain of JA2 propellant.




Figure 11. Cross section of surface layers of laser-irradiated grain of JA2 propellant.




Figure 12. FTIR microscope spectrum of irradiated portion of grain of M9 propellant.




Figure 13. FTIR microscope spectra of (a) laser-irradiated M9 (sample no. 115, Table 2) propellant; (b) burned/extinguished M9 propellant (Schroeder et al. 1994); and (c) virgin M9 propellant.




Figure 14. FTIR microscope spectra of (a) virgin JA2 propellant; (b) laser-irradiated JA2 propellant (sample no. 24, Table 2); and (c) burned/extinguished JA2 propellant (Schroeder et al. 1994).




Figure 15. FTIR microscope spectrum of virgin XM39 propellant.




Figure 16. FTIR-microscope spectra of (a) laser-irradiated (sample no. 58, Table 2) XM39 propellant; (b) laser-irradiated (sample no. 33, Table 2) XM39 propellant; and (c) virgin XM39 propellant.

INTENTIONALLY LEFT BLANK.

6. REFERENCES

- Beyer, R. A., and A. C. Cohen. "Small Scale Experiments and Modelling of Laser Ignition of Gun Propellants." Army Science: The New Frontiers. Military and Civilian Applications. Saratoga, WY: Borg Biomedical Books, pp. 529-544, 1993.
- Gordon, A. J., and R. A. Ford. The Chemist's Companion: A Handbook of Practical Data, Techniques and References. New York: Wiley-Interscience, pp. 196-197, 1972.
- Ostmark, H., and R. Grans. "Laser Ignition of Explosives: Effects of Gas Pressure on the Threshold Ignition Energy." Journal of Energetic Materials, vol. 8, pp. 308-322, 1990.
- Ostrowski, P. P., J. F. Grant, J. Sharma, W. L. Garrett, D. S. Downs, and S. Krasner. "Laser Ignition of Double and Triple Based Gun Propellants." Proceedings of the 17th JANNAF Combustion Meeting, Hampton, VA, CPIA Publication No. 329, vol. II, pp. 175-187, September 1980.
- Schroeder, M. A., R. A. Fifer, M. S. Miller, and R. A. Pesce-Rodriguez. "Condensed-Phase Processes During Solid-Propellant Combustion. I. Preliminary Chemical and Microscopic Examination of Extinguished Propellant Samples." BRL-MR-3845, U.S. Army Ballistic Research Laboratory, Aberdeen Proving Ground, MD, June 1990.
- Schroeder, M. A., R. A. Fifer, M. S. Miller, R. A. Pesce-Rodriguez, and G. Singh. "Condensed-Phase Processes During Solid-Propellant Combustion. II. Chemical and Microscopic Examination of Conductively-Quenched Samples of RDX, XM39, JA2, M30, and HMX-Binder Compositions." BRL-TR-3337, U.S. Army Ballistic Research Laboratory, Aberdeen Proving Ground, MD, May 1992.
- Schroeder, M. A., R. A. Fifer, M. S. Miller, R. A. Pesce-Rodriguez, C. J. Selawski, and G. Singh. "Condensed Phase Processes During Solid Propellant Combustion. III. Some Preliminary Depth Profiling Studies on XM39, JA2, M9, and HMX2." ARL-TR-346, U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, January 1994.
- Silverstein, R. M., G. C. Bassler, and T. C. Morrill. Spectrometric Identification of Organic Compounds. 5th edition, New York: Wiley, pp. 113-117, 1991.

INTENTIONALLY LEFT BLANK.

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	ADMINISTRATOR ATTN DTIC DDA DEFENSE TECHNICAL INFO CTR CAMERON STATION ALEXANDRIA VA 22304-6145
1	DIRECTOR ATTN AMSRL OP SD TA US ARMY RESEARCH LAB 2800 POWDER MILL RD ADELPHI MD 20783-1145
3	DIRECTOR ATTN AMSRL OP SD TL US ARMY RESEARCH LAB 2800 POWDER MILL RD ADELPHI MD 20783-1145
1	DIRECTOR ATTN AMSRL OP SD TP US ARMY RESEARCH LAB 2800 POWDER MILL RD ADELPHI MD 20783-1145
	<u>ABERDEEN PROVING GROUND</u>
5	DIR USARL ATTN AMSRL OP AP L (305)

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	HQDA ATTN SARD TT DR F MILTON PENTAGON WASHINGTON DC 20310-0103
1	HQDA ATTN SARD TT MR J APPEL PENTAGON WASHINGTON DC 20310-0103
1	HQDA OASA RDA ATTN DR C H CHURCH PENTAGON ROOM 3E486 WASHINGTON DC 20310-0103
4	COMMANDER ATTN R GHIRARDELLI D MANN R SINGLETON R SHAW US ARMY RESEARCH OFFICE P O BOX 12211 RSCH TRNGLE PK NC 27709-2211
1	DIRECTOR ATTN AMXRO MCS K CLARK ARMY RESEARCH OFFICE P O BOX 12211 RSCH TRNGLE PK NC 27709-2211
1	DIRECTOR ATTN AMXRO RT IP LIB SERVICES ARMY RESEARCH OFFICE P O BOX 12211 RSCH TRNGLE PK NC 27709-2211
1	COMMANDER ATTN SMCAR AEE B D S DOWNS US ARMY ARDEC PCTNY ARSNL NJ 07806-5000
1	COMMANDER ATTN SMCAR AEE J A LANNON US ARMY ARDEC PCTNY ARSNL NJ 07806-5000
1	COMMANDER ATTN SMCAR AEE WW S BULUSU US ARMY ARDEC PCTNY ARSNL NJ 07806-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	COMMANDER ATTN SMCAR AEE WE T CHEN US ARMY ARDEC PCTNY ARSNL NJ 07806-5000
1	COMMANDER ATTN SMCAR AEE BR L HARRIS US ARMY ARDEC PCTNY ARSNL NJ 07806-5000
2	COMMANDER ATTN AMSMI RD PR E A R MAYKUT AMSMI RD PR P R BETTS US ARMY MISSILE COMMAND REDSTONE ARSENAL AL
1	OFFICE OF NAVAL RESEARCH ATTN R S MILLER CODE 432 DEPARTMENT OF THE NAVY 800 N QUINCY STREET ARLINGTON VA 22217
1	COMMANDER ATTN J RAMNARACE AIR 54111C NAVAL AIR SYSTEMS COMMAND WASHINGTON DC 20360
2	COMMANDER ATTN R BERNECKER R 13 G B WILMOT R 16 NAVAL SURFACE WARFARE CENTER SILVER SPRING MD 20903-5000
5	COMMANDER ATTN M C LIN J MCDONALD E ORAN J SHNUR R J DOYLE CODE 6110 NAVAL RESEARCH LABORATORY WASHINGTON DC 20375
2	COMMANDER ATTN T BOGGS CODE 388 T PARR CODE 3895 NAVAL WEAPONS CENTER CHINA LAKE CA 93555-6001

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	SUPERINTENDENT ATTN D W NETZER DEPT OF AERONAUTICS NAVAL POSTGRADUATE SCHOOL MONTEREY CA 93940
3	AL LSCF ATTN R CORLEY R GEISLER J LEVINE EDWARDS AFB CA 93523-5000
1	AFOSR ATTN J M TISHKOFF BOLLING AIR FORCE BASE WASHINGTON DC 20332
1	OSD SDIO IST ATTN L CAVENY PENTAGON WASHINGTON DC 20301-7100
1	COMMANDANT ATTN ATSF TSM CN USAFAS FORT SILL OK 73503-5600
1	UNIV OF DAYTON RSCH INSTITUTE ATTN D CAMPBELL AL PAP EDWARDS AFB CA 93523
1	NASA ATTN G B NORTHAM MS 168 LANGLEY RESEARCH CENTER LANGLEY STATION HAMPTON VA 23365
4	NATIONAL BUREAU OF STANDARDS ATTN J HASTIE M JACOX T KASHIWAGI H SEMERJIAN US DEPARTMENT OF COMMERCE WASHINGTON DC 20234
2	DIRECTOR ATTN C WESTBROOK W TAO MS L 282 LAWRENCE LIVERMORE NATIONAL LAB P O BOX 808 LIVERMORE CA 94550

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	DIRECTOR ATTN B NICHOLS T7 MS B284 LOS ALAMOS NATIONAL LAB P O BOX 1663 LOS ALAMOS NM 87545
1	NATIONAL SCIENCE FOUNDATION ATTN A B HARVEY WASHINGTON DC 20550
2	PRINCETON COMBUSTION RESEARCH LABORATORIES INC ATTN N A MESSINA M SUMMERFIELD PRINCETON CORPORATE PLAZA BLDG IV SUITE 119 11 DEERPARK DRIVE MONMOUTH JUNCTION NJ 08852
4	DIRECTOR ATTN R CATTOLICA S JOHNSTON P MATTERN D STEPHENSON DIVISION 8354 SANDIA NATIONAL LABORATORIES LIVERMORE CA 94550
1	DIRECTOR ATTN R SKYOCYPEC DIVISION 1513 SANDIA NATIONAL LABORATORIES LIVERMORE CA 94550
1	BRIGHAM YOUNG UNIVERSITY ATTN M W BECKSTEAD DEPT OF CHEMICAL ENGINEERING PROVO UT 84058
1	CALIFORNIA INSTITUTE OF TECH ATTN L STRAND MS 125 224 JET PROPULSION LABORATORY 4800 OAK GROVE DRIVE PASADENA CA 91109
1	CALIFORNIA INSTITUTE OF TECHNOLOGY ATTN F E C CULICK MC 301 46 204 KARMAN LAB PASADENA CA 91125

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	UNIVERSITY OF CALIFORNIA LOS ALAMOS SCIENTIFIC LAB P O BOX 1663 MAIL STOP B216 LOS ALAMOS NM 87545	3	GEORGIA INSTITUTE OF TECHNOLOGY ATTN E PRICE W C STRAHLE B T ZINN SCHOOL OF AEROSPACE ENGINEERING ATLANTA GA 30332
1	UNIVERSITY OF CALIFORNIA BERKELEY ATTN C BRADLEY MOORE CHEMISTRY DEPARTMENT 211 LEWIS HALL BERKELEY CA 94720	1	UNIVERSITY OF ILLINOIS ATTN H KRIER DEPT OF MECH ENG 144MEB 1206 W GREEN ST URBANA IL 61801
1	UNIVERSITY OF CALIFORNIA SAN DIEGO ATTN F A WILLIAMS AMES B010 LA JOLLA CA 92093	1	THE JOHNS HOPKINS UNIV CPIA ATTN T W CHRISTIAN 10630 LITTLE PATUXENT PKWY SUITE 202 COLUMBIA MD 21044-3200
2	UNIV OF CALIFORNIA SANTA BARBARA ATTN K SCHOFIELD M STEINBERG QUANTUM INSTITUTE SANTA BARBARA CA 93106	1	UNIV OF MD EASTERN SHORE ATTN G SINGH DEPT OF NATURAL SCIENCES PRINCESS ANNE MD 21853-1299
1	UNIV OF COLORADO AT BOULDER ENGINEERING CENTER ATTN J DAILY CAMPUS BOX 427 BOULDER CO 80309-0427	1	UNIVERSITY OF MICHIGAN ATTN G M FAETH GAS DYNAMICS LAB AEROSPACE ENGINEERING BLDG ANN ARBOR MI 48109-2140
3	UNIV OF SOUTHERN CALIFORNIA ATTN R BEAUDET S BENSON C WITTIG DEPT OF CHEMISTRY LOS ANGELES CA 90007	1	UNIVERSITY OF MINNESOTA ATTN E FLETCHER DEPT OF MECHANICAL ENGINEERING MINNEAPOLIS MN 55455
1	CORNELL UNIVERSITY ATTN T A COOL DEPT OF CHEMISTRY BAKER LABORATORY ITHACA NY 14853	4	PENNSYLVANIA STATE UNIVERSITY ATTN K KUO M MICCI S THYNELL V YANG DEPT OF MECHANICAL ENGINEERING UNIVERSITY PARK PA 16802
1	UNIVERSITY OF DELAWARE ATTN T BRILL CHEMISTRY DEPARTMENT NEWARK DE 19711	1	POLYTECHNIC INSTITUTE OF NY ATTN S LEDERMAN GRADUATE CENTER ROUTE 110 FARMINGDALE, NY 11735
1	UNIVERSITY OF FLORIDA ATTN J WINEFORDNER DEPT OF CHEMISTRY GAINESVILLE FL 32611		

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	PRINCETON UNIVERSITY ATTN K BREZINSKY I GLASSMAN FORRESTAL CAMPUS LIBRARY P O BOX 710 PRINCETON NJ 08540	2	APPLIED MECHANICS REVIEWS ATTN R E WHITE A B WENZEL ASME 345 E 47TH STREET NEW YORK NY 10017
1	PURDUE UNIVERSITY ATTN J R OSBORN SCHOOL OF AERONAUTICS & ASTRONAUTICS GRISSOM HALL WEST LAFAYETTE IN 47906	1	ATLANTIC RESEARCH CORP ATTN R H W WAESCHE 7511 WELLINGTON ROAD GAINESVILLE VA 22065
1	PURDUE UNIVERSITY ATTN E GRANT DEPARTMENT OF CHEMISTRY WEST LAFAYETTE IN 47906	1	TEXTRON DEFENSE SYSTEMS ATTN A PATRICK 2385 REVERE BEACH PARKWAY EVERETT MA 02149-5900
2	PURDUE UNIVERSITY ATTN N M LAURENDEAU S N B MURTHY SCHOOL OF MECHANICAL ENGINEERING TSPC CHAFFEE HALL WEST LAFAYETTE IN 47906	1	BATTELLE TWSTIAC 505 KING AVENUE COLUMBUS OH 43201-2693
1	RENSSELAER POLYTECHNIC INST ATTN A FONTIJN DEPT OF CHEMICAL ENGINEERING TROY NY 12181	1	COHEN PROFESSIONAL SERVICES ATTN N S COHEN 141 CHANNING STREET REDLANDS CA 92373
1	STANFORD UNIVERSITY ATTN R HANSON DEPT OF MECHANICAL ENGINEERING STANFORD CA 94305	1	EXXON RESEARCH & ENG CO ATTN A DEAN ROUTE 22E ANNANDALE NJ 08801
1	UNIVERSITY OF TEXAS ATTN W GARDINER DEPT OF CHEMISTRY AUSTIN TX 78712	1	GENERAL APPLIED SCIENCE LABS INC 77 RAYNOR AVENUE RONKONKAMA NY 11779-6649
1	VA POLYTECH INST AND STATE UNIV ATTN J A SCHETZ BLACKSBURG VA 24061	1	GENERAL ELECTRIC ORDNANCE SYSTEMS ATTN J MANDZY 100 PLASTICS AVENUE PITTSFIELD MA 01203
1	APPLIED COMBUSTION TECHNOLOGY INC ATTN A M VARNEY P O BOX 607885 ORLANDO FL 32860	1	GENERAL MOTORS RSCH LABS ATTN T SLOANE PHYSICAL CHEMISTRY DEPARTMENT WARREN MI 48090-9055
		2	HERCULES INC ATTN W B WALKUP E A YOUNT P O BOX 210 ROCKET CENTER WV 26726

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	HERCULES INC ATTN R V CARTWRIGHT 100 HOWARD BLVD KENVIL NJ 07847
1	ALLIANT TECHSYSTEMS INC ATTN D E BRODEN MS MN50 2000 MARINE SYSTEMS GROUP 600 2ND STREET NE HOPKINS MN 55343
1	ALLIANT TECHSYSTEMS INC ATTN R E TOMPKINS MN 11 2720 600 SECOND ST NORTH HOPKINS MN 55343
1	IBM CORPORATION ATTN A C TAM RESEARCH DIVISION 5600 COTTLE ROAD SAN JOSE CA 95193
1	IIT RESEARCH INSTITUTE ATTN R F REMALY 10 WEST 35TH STREET CHICAGO IL 60616
1	LOCKHEED MISSILES & SPACE CO ATTN GEORGE LO 3251 HANOVER STREET DEPT 52 35 B204 2 PALO ALTO CA 94304
1	OLIN ORDNANCE ATTN V MCDONALD LIBRARY P O BOX 222 ST MARKS FL 32355-0222
1	PAUL GOUGH ASSOCIATES INC ATTN P S GOUGH 1048 SOUTH STREET PORTSMOUTH NH 03801-5423
1	HUGHES AIRCRAFT COMPANY ATTN T E WARD 8433 FALLBROOK AVENUE CANOGA PARK CA 91303

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	MBR RESEARCH INC ATTN M BEN REUVEN SUITE C22 801 EWING STREET PRINCETON NJ 08540
1	NM INST OF MINING & TECH ATTN J OXLEY DEPT OF CHEMISTRY SOCORRO NM 87801
1	ROCKWELL INTERNATIONAL CORP ATTN J E FLANAGAN HB02 ROCKETDYNE DIVISION 6633 CANOGA AVENUE CANOGA PARK CA 91304
1	SCIENCE APPLICATIONS INC ATTN R B EDELMAN 23146 CUMORAH CREST WOODLAND HILLS CA 91364
3	SRI INTERNATIONAL ATTN G SMITH D CROSLEY D GOLDEN 333 RAVENSWOOD AVENUE MENLO PARK CA 94025
1	STEVENS INSTITUTE OF TECH ATTN R MCALEVY III DAVIDSON LABORATORY HOBOKEN NJ 07030
1	SVERDRUP TECHNOLOGY INC ATTN R J LOCKE MS SVR 2 LERC GROUP 2001 AEROSPACE PARKWAY BROOK PARK OH 44142
1	SVERDRUP TECHNOLOGY INC ATTN J DEUR 2001 AEROSPACE PARKWAY BROOK PARK OH 44142
3	THIOKOL CORPORATION ATTN R BIDDLE R WILLER TECH LIB ELKTON DIVISION P O BOX 241 ELKTON MD 21921

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
3	THIOKOL CORPORATION ATTN S J BENNETT WASATCH DIVISION P O BOX 524 BRIGHAM CITY UT 84302
1	UNITED TECHNOLOGIES RSCH CENTER ATTN A C ECKBRETH EAST HARTFORD CT 06108
1	UNITED TECHNOLOGIES CORP ATTN R R MILLER CHEMICAL SYSTEMS DIVISION P O BOX 49028 SAN JOSE CA 95161-9028
1	UNIVERSAL PROPULSION COMPANY ATTN H J MCSPADDEN 25401 NORTH CENTRAL AVENUE PHOENIX AZ 85027-7837
1	VERITAY TECHNOLOGY INC ATTN E B FISHER 4845 MILLERSPORT HIGHWAY EAST AMHERST NY 14051-0305
1	FREEDMAN ASSOCIATES ATTN E FREEDMAN 2411 DIANA ROAD BALTIMORE MD 21209-1525
1	ALLIANT TECHSYSTEMS ATTN J BODE 600 SECOND ST NE HOPKINS MN 55343
1	ALLIANT TECHSYSTEMS ATTN C CANDLAND 600 SECOND ST NE HOPKINS MN 55343
1	ALLIANT TECHSYSTEMS ATTN L OSGOOD 600 SECOND ST NE HOPKINS MN 55343
1	ALLIANT TECHSYSTEMS ATTN R BURETTA 600 SECOND ST NE HOPKINS MN 55343

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	ALLIANT TECHSYSTEMS ATTN R BECKER 600 SECOND ST NE HOPKINS MN 55343
1	ALLIANT TECHSYSTEMS ATTN M SWENSON 600 SECOND ST NE HOPKINS MN 55343
1	US ARMY BENET LABORATORY ATTN SAM SOPOK SMCAR CCB B WATERVLIET NY 12189

NO. OF
COPIES ORGANIZATION

ABERDEEN PROVING GROUND

36 DIR USARL
ATTN: AMSRL-WT-P, A HORST
AMSRL-WT-PC,
R A FIFER
G F ADAMS
W R ANDERSON
R A BEYER
S W BUNTE
C F CHABALOWSKI
K P MC-NEILL BOONSTOPPEL
A COHEN
R CUMPTON
R DANIEL
D DEVYNCK
N F FELL
B E FORCH
J M HEIMERL
A J KOTLAR
M R MANAA
W F MCBRATNEY
K L MCNESBY
S V MEDLIN
M S MILLER
A W MIZIOLEK
S H MODIANO
J B MORRIS
J E NEWBERRY
S A NEWTON
R A PESCE-RODRIGUEZ
B M RICE
R C SAUSA
M A SCHROEDER
J A VANDERHOFF
M WENSING
A WHREN
J M WIDDER
C WILLIAMSON
AMSRL-CI-CA, R PATEL

USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. ARL Report Number ARL-TR-781 Date of Report July 1995
2. Date Report Received _____
3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) _____

4. Specifically, how is the report being used? (Information source, design data, procedure, source of ideas, etc.) _____

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided, or efficiencies achieved, etc? If so, please elaborate. _____

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) _____

CURRENT
ADDRESS

Organization

Name

Street or P.O. Box No.

City, State, Zip Code

7. If indicating a Change of Address or Address Correction, please provide the Current or Correct address above and the Old or Incorrect address below.

OLD
ADDRESS

Organization

Name

Street or P.O. Box No.

City, State, Zip Code

(Remove this sheet, fold as indicated, tape closed, and mail.)
(DO NOT STAPLE)

DEPARTMENT OF THE ARMY


OFFICIAL BUSINESS

BUSINESS REPLY MAIL

FIRST CLASS PERMIT NO 0001,APG,MD

POSTAGE WILL BE PAID BY ADDRESSEE

**DIRECTOR
U.S. ARMY RESEARCH LABORATORY
ATTN: AMSRL-WT-PC
ABERDEEN PROVING GROUND, MD 21005-5066**



**NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES**

